

Material

EPDM EP702201

black

cross linking: peroxidic

revision index	revision date			page
2	9/27/2018			1 / 2
Physical properties		nominal range	typical values	
Density DIN ISO 1183		1.20 ±0.03	1.20	g/cm ³
Hardness DIN ISO 7619, Shore A		70 ±5	71	Shore
Tensile strength DIN 53504		---	>= 15	MPa
Elongation at break DIN 53504		---	>= 300	%
Compression set DIN ISO 815 B, 24 h, 70 °C		---	16	%
Abrasion DIN 53516		---	120	mm ³
Rebound resilience DIN 53512		---	37	%
Temperature range	-45°C to 150°C			
Declarations of conformity				
	Country	Part	Remark	Expires unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)	<input checked="" type="checkbox"/>

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner
 Telefon: +49 40 66989 279
 Fax: +49 40 66989 9279
 Email: nadja.gueldner@fst.com

Material EPDM EP702201

black

cross linking: peroxidic

revision index

2

revision date

9/27/2018

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH

Global Material Technology

Nadja Güldner

Telefon: +49 40 66989 279

Fax: +49 40 66989 9279

Email: nadja.gueldner@fst.com