

Technical data sheet in accordance with ASTM

# Material

## NBR NB703409

black

cross linking: sulfur

<b>revision index</b>	<b>revision date</b>	<b>page</b>	1 / 2
2	7/3/2017		

Physical properties	nominal range	typical values	
<b>Density</b> ASTM D 1817	1.26 ±0.02	1.26	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240, Shore A	70 ±5	70	Shore
<b>Tensile strength</b> ASTM D412	---	16.7	MPa
<b>Elongation at Break</b> ASTM D412	---	445	%
<b>Low temperature test</b> ASTM D1329, TR10	---	-30	°C
<b>Tear strength</b> ASTM D 624, C	---	58	KN/m
<b>Compression set</b> ASTM D395, B, 22 h, 100 °C, 25 %	---	13	%
<b>Low-temperature resistance</b> ASTM D 2137, 3 min, pass	---	-40	

### Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner  
 Telefon: +49 40 66989 279  
 Fax: +49 40 66989 9279  
 Email: nadja.gueldner@fst.com

Technical data sheet in accordance with ASTM

## **Material**

### **NBR NB703409**

black

cross linking: sulfur

**revision index**

2

**revision date**

7/3/2017

**page** 2 / 2

### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH

Global Material Technology

Nadja Güldner

Telefon: +49 40 66989 279

Fax: +49 40 66989 9279

Email: [nadja.gueldner@fst.com](mailto:nadja.gueldner@fst.com)