

Material

75 FKM 181327

green

revision index

5

revision date

9/22/2016

page

1 / 2

Physical properties

| | nominal range | typical values | |
|---|----------------|----------------|-------------------|
| Density DIN EN ISO 1183-1 | 2.04 ±0.03 | 2.05 | g/cm ³ |
| Hardness DIN ISO 7619-1 | 75 ±5 | 72 | Shore |
| Rebound resilience DIN 53512 | --- | 6 | % |
| Modulus 100 %, DIN 53504, S2 | > 6 | 8 | MPa |
| Tensile strength DIN 53504, S2 | > 12 | 14.5 | MPa |
| Elongation at break DIN 53504, S2 | > 150 | 220 | % |
| Compression set DIN ISO 815, B, 22 h, 175 °C | < 15 | 8 | % |
| Compression set DIN ISO 815, B, 22 h, 175 °C, in der Prüfkammer abgekühlt | < 30 | 16 | % |
| Low Temperature ISO 11357-2, DSC | --- | -17 | °C |
| Temperature range | -20°C to 200°C | | |

Declarations of conformity

| | Country | Part | Remark | Expires | unlimited |
|--------------|---------|------|--|---------|-------------------------------------|
| RoHS conform | | | including EU 2011/65 and EU2015/863 (ROHS III) | | <input checked="" type="checkbox"/> |

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker
Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

Material 75 FKM 181327

green

revision index

5

revision date

9/22/2016

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com