

Material

FKM FP754101

black

cross linking: bisphenolically

revision index

3

revision date

2/26/2020

page

1 / 2

Physical properties

Density

DIN EN ISO 1183-1

nominal range

1.92 ±0.02

typical values

g/cm³

Hardness

DIN ISO 7619-1, Shore A

75 ±5

75

Shore

Tensile strength

DIN 53504

≥ 8

MPa

Elongation at break

DIN 53504

≥ 150

%

Tear strength

DIN ISO 34-1 C

≥ 25

KN/m

Compression set

DIN ISO 815, B, 22 h, 200 °C, 25 %

≥ 20

%

Low temperature test

ASTM D1329, TR10

≤ -10

°C

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

Freudenberg

Freudenberg Industrial Services GmbH

Global Material Technology

Nadja Güldner

Telefon: +49 40 66989 279

Fax: +49 40 66989 9279

Email: nadja.gueldner@fst.com

Material

FKM FP754101

black

cross linking: bisphenolically

revision index

3

revision date

2/26/2020

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH

Global Material Technology

Nadja Güldner

Telefon: +49 40 66989 279

Fax: +49 40 66989 9279

Email: nadja.gueldner@fst.com