

Technical data sheet in accordance with ASTM

Material

NBR NB751601

black

cross linking: sulfur

revision index	revision date	page	1 / 2
1	11/7/2017		

Physical properties	nominal range	typical values	
Density ASTM D 792	1.20 ±0.02	1.20	g/cm ³
Hardness ASTM D 2240, Shore A	75 ±5	75	Shore
Tensile strength ASTM D 412	---	18	MPa
Elongation at Break ASTM D 412	---	290	%
Tear strength ASTM D 624 B	---	53	KN/m
Low temperature test ASTM D 2137, brittleness point	---	-20	°C
Compression set ASTM D 395 B, 22 h, 100 °C	---	7	%

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

Freudenberg

Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH
 Global Material Technology
 Viviane Rellstab
 Telefon: +49 40 66989 316
 Fax: +49 40 66989 9316
 Email: Viviane.Rellstab@dichtomatik.de

Technical data sheet in accordance with ASTM

Material

NBR NB751601

black

cross linking: sulfur

revision index

1

revision date

11/7/2017

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH

Global Material Technology

Viviane Rellstab

Telefon: +49 40 66989 316

Fax: +49 40 66989 9316

Email: Viviane.Rellstab@dichtomatik.de