

Material

NBR NB800901

black

revision index

1

revision date

9/26/2017

page

1 / 3

Physical properties

	nominal range	typical values	
Density	---	1.27	g/cm ³
Hardness BS ISO 48	80 ±5	80	IRHD
Tensile strength BS ISO 37	---	15.8	MPa
Elongation at break BS ISO 37	---	243	%
Compression set BS ISO 815, 22 h, 100 °C	---	17.5	%

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

Change after aging in Air: 70h/100°C

		Typ. values		
		Base value	After aging	difference
Hardness (BS ISO 48)	IRHD	80	78.6	-1
Tensile strength (BS ISO 37)	MPa	15.8	17.8	12 %
Elongation at break (BS ISO 37)	%	243	184	-24 %

Change after aging in ASTM-Oil No. 1: 70h/100°C

		Typ. values		
		Base value	After aging	difference
Hardness (BS ISO 48)	IRHD	80	82.3	2
Tensile strength (BS ISO 37)	MPa	15.8	18.7	18 %
Elongation at break (BS ISO 37)	%	243	199.5	-18 %
volume change (BS ISO 815 / 1817)	%		-7.5	%

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner
 Telefon: +49 40 66989 279
 Fax: +49 40 66989 9279
 Email: naja.gueldner@fst.com

Material

NBR NB800901

black

revision index

1

revision date

9/26/2017

page 2 / 3

Change after aging in ASTM-Oil No. 3: 70h/100°C

Typ. values

		Base value	After aging	difference
Hardness (BS ISO 48)	IRHD	80	77.4	-3
Tensile strength (BS ISO 37)	MPa	15.8	17.3	10 %
Elongation at break (BS ISO 37)	%	243	218	-10 %
volume change (BS ISO 815 / 1817)	%		5	%

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: +49 40 66989 279
Fax: +49 40 66989 9279
Email: nadja.gueldner@fst.com

Material

NBR NB800901

black

revision index

1

revision date

9/26/2017

page

3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: +49 40 66989 279
Fax: +49 40 66989 9279
Email: nadja.gueldner@fst.com