

Material

85 AU 21030

violet

revision index

2

revision date

7/9/2015

page

1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	1.13 ±0.02	1.13	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	86 ±5	86	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	> 6	6.5	MPa
Modulus 300 %, DIN 53504, S2, 23 °C	---	11	MPa
Tensile strength DIN 53504, S2, 23 °C	> 45	57	MPa
Elongation at break DIN 53504, S2, 23 °C	> 450	575	%
Tear strength DIN ISO 34-1, B (b), 23 °C	---	57	KN/m
Compression set DIN ISO 815, 24 h, 70 °C, 15 %	---	25	%
Compression set DIN ISO 815, 24 h, 100 °C, 20 %	---	42	%
Compression set DIN ISO 815, 70 h, 100 °C, 15 %	---	63	%
Low Temperature ISO 11357-2, DSC	---	-47	°C
Torsions pendulum test DIN EN ISO 6721-2A	---	-31	°C
Temperature range	-35°C to 100°C		

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer
Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com

Material 85 AU 21030

violet

revision index

2

revision date

7/9/2015

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer

Telefon: +49 6201 80 2182

Fax: +49 6201 88 2182

Email: Daniel.Danzer@fst.com