

Material

88 NBR 101

black

cross linking: sulfur

revision index

8

revision date

9/1/2016

page

1 / 3

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	1.41 ±0.02	1.41	g/cm ³
Hardness DIN ISO 7619-1	88 ±5	90	Shore
Rebound resilience DIN 53512	---	17	%
Modulus 100 %, DIN 53504, S2	8	9.8	MPa
Tensile strength DIN 53504, S2	> 10	13.5	MPa
Elongation at break DIN 53504, S2	> 170	215	%
Compression set DIN ISO 815, 22 h, 100 °C	< 60	43	%
Low Temperature ISO 11357-2, DSC	---	-28	°C
Temperature range	-30°C to 100°C		

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com

Material

88 NBR 101

black

cross linking: sulfur

revision index

8

revision date

9/1/2016

page 2 / 3

Tested after ASTM D 2000: M 7 BG 910 B14 EA14 EF11 EF21 EO14 EO34

		nominal range	typical values
Hardness	Shore	90 ±5	90
Tensile strength	MPa	min. 10	14
Elongation at break	%	min. 100	200
Change after aging in Air 70h/100°C			
Hardness	Shore A	---	3
Tensile strength	%	---	9
Elongation at break	%	---	-30
B14 Compression set 22h/100°C	%	25	23
EA14 Change after aging in Distilled water 70h/100°C			
Hardness	Shore A	±10	-3
Volume	%	±15	4
EF11 Change after aging in Fuel A 70h/23°C			
Hardness	Shore A	±10	2
Tensile strength	%	-25	-8
Elongation at break	%	-25	-10
Volume	%	-5 to 10	3
EF21 Change after aging in Fuel B 70h/23°C			
Hardness	Shore A	0 to -30	-20
Tensile strength	%	-60	-30
Elongation at break	%	-60	-25
Volume	%	0 to 40	30
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore A	±5	4
Tensile strength	%	-25	8

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com

Material
88 NBR 101

black

cross linking: sulfur

revision index	revision date		page	3 / 3
8	9/1/2016			
Elongation at break		%	-45	-25
Volume		%	-10 to 5	-3
EO34 Change after aging in IRM 903 70h/100°C				
Hardness		Shore A	-10 to 5	-10
Tensile strength		%	-45	4
Elongation at break		%	-45	-18
Volume		%	0 to 25	13

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com