

Technical data sheet in accordance with ASTM

# Material

## TPU PU905501

blue

**revision index**

1

**revision date**

9/26/2017

**page**

1 / 2

### Physical properties

	<b>nominal range</b>	<b>typical values</b>	
<b>Density</b> ASTM D 1817	1.14 ±0.03	1.14	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240, Shore A	90 ±5	90	Shore
<b>Tensile strength</b> ASTM D412	---	36.4	MPa
<b>Elongation at Break</b> ASTM D412	---	498	%
<b>Compression set</b> ASTM D395, B, 22 h, 100 °C	---	33.6	%

### Declarations of conformity

	<b>Country</b>	<b>Part</b>	<b>Remark</b>	<b>Expires</b>	<b>unlimited</b>
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner  
 Telefon: +49 40 66989 279  
 Fax: +49 40 66989 9279  
 Email: [nadja.gueldner@fst.com](mailto:nadja.gueldner@fst.com)

Technical data sheet in accordance with ASTM

## **Material**

### **TPU PU905501**

blue

**revision index**

1

**revision date**

9/26/2017

**page**

2 / 2

### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH

Global Material Technology

Nadja Güldner

Telefon: +49 40 66989 279

Fax: +49 40 66989 9279

Email: [nadja.gueldner@fst.com](mailto:nadja.gueldner@fst.com)