

# Material

## 95 AU V149

blue

<b>revision index</b>	<b>revision date</b>	<b>page</b>	1 / 2
5	1/12/2016		

Physical properties	nominal range	typical values	
<b>Density</b> DIN EN ISO 1183-1, 23 °C	1.20 ±0.02	1.20	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 7619-1, Shore A, 23 °C	94 ±3	94	Shore
<b>Hardness</b> DIN ISO 7619-1, Shore D, 23 °C	45 ±5	45	Shore
<b>Modulus</b> 100 %, DIN 53504, S2, 23 °C	> 10	12.5	MPa
<b>Modulus</b> 300 %, DIN 53504, S2, 23 °C	---	21	MPa
<b>Tensile strength</b> DIN 53504, S2, 23 °C	> 30	43	MPa
<b>Elongation at break</b> DIN 53504, S2, 23 °C	> 400	530	%
<b>Tear strength</b> DIN ISO 34-1, B (b), 23 °C	---	100	KN/m
<b>Compression set</b> DIN ISO 815, 24 h, 100 °C, 20 %	---	36	%
<b>Low Temperature</b> ISO 11357-2, DSC	---	-37	°C
<b>Temperature range</b>	-30°C to 100°C		

### Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

### Freudenberg

Freudenberg FST GmbH  
Global Material Technology  
Wolfgang Becker  
Telefon: +49 (0)6201/80-2893  
Fax: +49 (0)6201/88-2893  
Email: wolfgang.becker@FST.com

**Material**  
**95 AU V149**

blue

**revision index**

5

**revision date**

1/12/2016

**page**

2 / 2

**No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

**Freudenberg**

Freudenberg FST GmbH  
Global Material Technology  
Wolfgang Becker

Telefon: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: [wolfgang.becker@FST.com](mailto:wolfgang.becker@FST.com)