

Material 98 AU 928

revision index	revision date	page	1 / 3
5	7/9/2015		

Physical properties	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	1.19 ±0.02	1.19	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	97 ±3	97	Shore
Hardness DIN ISO 7619-1, Shore D, 23 °C	55 ±4	55	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	> 18	20.8	MPa
Modulus 300 %, DIN 53504, S2, 23 °C	---	31	MPa
Tensile strength DIN 53504, S2, 23 °C	> 48	57	MPa
Elongation at break DIN 53504, S2, 23 °C	> 350	456	%
Tear strength DIN ISO 34-1, B (b), 23 °C	---	155	KN/m
Compression set DIN ISO 815, 24 h, 100 °C, 20 %	---	35	%
Compression set DIN ISO 815, 70 h, 100 °C, 10 %	---	39	%
Compression set DIN ISO 815, 24 h, 125 °C, 10 %	---	55	%
Low Temperature ISO 11357-2, DSC	---	-39	°C
Torsions pendulum test DIN EN ISO 6721-2A	---	-17	°C
Temperature range	-30°C to 110°C		

Declarations of conformity

RoHS conform	Country	Part	Remark	Expires	unlimited
			including EU 2011/65 and		<input checked="" type="checkbox"/>

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer
Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com

Material
98 AU 928

revision index
5

revision date
7/9/2015

page 2 / 3

Country Part

Remark
EU2015/863 (ROHS III)

Expires unlimited

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer
Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com

Material 98 AU 928

revision index
5

revision date
7/9/2015

page 3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer
Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com